

Metalrex Metal Offset Printing Inks

Metalrex Metal offset printing inks are designed for the metal printing industry. Industry's considerations have been taken into account when formulating **Metalrex** in order to yield a tough but flexible cured ink film.

Recommended baking condition for **Metalrex** CMYK inks is 15 min @ 140~160°C. However, for optimal results, temperature can be varied from 120°C and up to 180°C.

FEATURES

- Quick and smooth ink transfer
- Excellent rub resistance
- Flexible ink film
- Color reproductibility: DE<2,5

FASTNESS

PROCESS COLORS		Light	Alkali	Alcohol
Magenta	1122	6	Y	Y
Yellow	1146	6	Y	Y
Cyan	1156	8	Y	Y
Black	1173	8	Y	Y

SUBSTRATES

Substrates	Tin	Aluminium	Foil
	Y	Y	C

Lightfastness (1: poor ~ 8:excellent)

Y: Yes

N: No

C: Caution



Tel: +961-4-865965 Fax: +961-4-865966

P.O.Box: 3, Broumana - LEBANON

E-mail: comex@technorexco.com